KPU International Journal of Engineering & Technology
Volume 2, Issue2, Dec. 2022
e-ISSN:2790-0819, p-ISSN:2790-0800
Date Received: 2022-10-10
Date Accepted: 2022-12-22
Date Published: 2022-12-30

A Review on Physical Properties of Nano-Concrete

NOORULLAH ZAHID*

*Assistant Professor, Department of Civil, Engineering Faculty, Shaikh Zayed University, Khost Town, Afghanistan. Email:zahidnoorullah@gmail.com

Abstract

All the properties of concrete are associated with the processes that occur at the nano-scale. In this study, the physical properties of nano-concrete are reviewed. Nano-concrete has nanoparticles (such as Nano SiO2, Nano Al2O3, NanoTiO2, Nano Fe2O3, Nano Fe3O4, Nano Clay, NanoZrO2 carbon nanotubes, nano-fibers, and carbon nano-fibers) as admixtures in small quantities as a percentage of the burden of the cement. Due to its excellent physical properties, nano-concrete is becoming more and more popular in practical engineering. To get a deep understanding of the physical properties of nano-concrete, researchers have done a lot of research in this area. In this review paper, the most common is used. The nanoparticles have effectiveness on concrete's physical performance such as strength, modulus of elasticity, durability, density, abrasion resistance, resistance to permeability, and water absorption and frost resistance. Nanoparticles improve the share of strength and modulus of elasticity with the relevancy of the control mixes. The microstructure of various varieties of concrete is significantly enhanced upon the addition of nanoparticles and as a result durability of concrete increases. The microstructure of concrete with nanoparticles is denser and more uniform than that of conventional concrete. The nanoparticles reduce porosity, increase the density of cement concrete, and thus show an improvement in resistance to permeability and water absorption than conventional concrete, and therefore the frost resistance of concrete is improved. The addition of nanoparticles to concrete mixes showed more abrasion resistance for concrete and mortar. The decrease in workability of concrete with nanoparticles may be compensated by using of superplasticizer in concrete mixes.

Keywords: Nano-concrete; Nanoparticles; Nanotechnology; Physical property.

* Corresponding Author

1. Introduction

Nanotechnology of concrete includes nanometer-scale renovation techniques to form a brand new adequate generation of cementitious composites with ideal physical behavior, with the assistance of which made the concrete with unique properties. The final word goal of concrete nanotechnology is that the studying of concrete at the nano-scale and also the studying of nanoparticles accustomed give better properties to concrete.

Among the changes that nano-cement and nano-cementing materials have brought in concrete technology is the increase in crack resistance, decrease within the curing time, increase in ductility, and also increase in its strength. These positive changes have led to the employment of nano cement in most industries. The nanoparticles like TiO_2, Al_2O_3, ZnO_2, SiO_2, carbon nanotubes, nanofibers, and carbon nanofibers can affect the mechanical and physical properties of cement concrete. When the cement particles mix, the combination is composed of holes from some micrometers to some millimeters, which is one of the explanations for the low strength of cement concrete. the employment of nanotechnology has solved this problem. So well that nano-crystals penetrate within the pores of cement mix and well cover the space between cement particles. This decreases the porosity and permeability which highly affect the standard of the concrete mix and increases its strength and durability [28].

Nanocrystals that fill nanopores will affect and increase their viscosity furthermore. On the opposite hand, nano cement granules and nano-particles are suspended in liquids and water and don't precipitate. This function allows for the preparation of a dense and suitable cement paste with nano-particles and cement. The very dense cement paste will positively affect the physical properties of cement concrete [44].

Nanomaterials such as nano silica, nano-TiO_2, Al_2O_3, ZnO_2, carbon nanotubes, nanofibers, etc. have the capability of improving the properties of concrete. It is clear that nanomaterials are still in their developing stages, and they have many challenges and unsolved complications for their huge commercial and application prospects. The main objective of this article is to study the incorporation of nanostructured materials in concrete mixes, which could improve the concrete's physical properties such as strength, modulus of elasticity, durability, density, abrasion resistance, resistance to permeability and water absorption, and frost resistance. The microstructures of concrete are significantly improved by the inclusion of nanomaterials, as the nanomaterials enhance the hydration process by generating more hydrated products.

2. Nano-concrete

Concrete is a construction material from an acceptable mixture of cement, water, sand, and gravel. Concrete is formed of cement paste (obtained from the chemical action of cement and water) and aggregates (sand and gravel) where the paste acts as a glue and binds the sand and gravel thus receiving concrete. In some cases it's necessary to feature some admixtures that are added to concrete in small quantities as a percentage of the burden of the cement, some part of them are nanoparticles, these nanoparticles are employed in concrete to urge some good properties like increasing strength, density, and durability of concrete. When nanoparticles are added to a concrete mixture as cement replacement in various percentages, this type of concrete is called nano-concrete [17].




Fig.1 The particle size and specific surface area scale related to concrete materials [39].

2.1. Differing types of nanoparticles used in concrete:

Nanoparticle refers to the ultrafine material with particle size at the nanometer level (1-100nm), which is larger than the atomic cluster (the cluster of atoms but 1nm in length) and smaller than the usual powder, within the transition zone of the cluster to the macroscopic object, a typical mesoscopic system. Because of its small size, large area, and other factors, have subsequent four special effects: size effect, quantum effect, surface effect, and interface effect. These four effects mainly reflect the structural, chemical, and physical characteristics of nanoparticles, which are called "the most promising materials of the 21st century".Nano-mineral powder mainly includes nano-silica, nano-calcium carbonate, and nano-silica powder. In ordinary hydraulic cement within the distribution

of 10-100nmgel pores, the incorporation of nano-powder just fills these gaps and plays a job in improving the permeability of concrete and toughness [44].

There are different types of nanoparticles utilized in concrete. There'll introduce the foremost important and widespread nanoparticles which are employed in cement concrete. These nanoparticles are usually made up of the cement itself, like nano iron, nano corundom, nano silica, etc. these nanoparticles have many advantages and downsides, and therefore the main problem of using these nanoparticles with cement concrete within the world belongs to them is that the economic discussion and their impact on the environment. For this reason, it's important to seek out the optimum and effective amount of those nanoparticles within the concrete and to search out nanoparticles that haven't any harmful effect on the environment [40]. Below are some current research results presented and reviewed. Sun et al, researched to change the impact of nano-silica on the concrete's initial compressive strength in large quantities of ash [40].

The results show that the nanoparticles are incorporated into the concrete, which might effectively improve the mechanical properties like compressive and flexural properties of concrete. The incorporation of nano-silica improves the mechanical properties of concrete much beyond that of nano-calcium carbonate. The explanation is that the volcanic ash activity of silica is far above that of silica fume, and also the incorporation of silica makes the slurry fluidity decrease and therefore the aggregation time is significantly shortened. At the identical time, the incorporation of nano-silica also can significantly improve the concrete early strength. Nano-silica puts into the cement, thanks to its structure, physical and chemical characteristics, and cement during a sizable amount of Ca(OH)2 combined, thereby promoting cement hydration, improving the reaction of the exothermic efficiency so the cement slurry micro-structure to boost the cement more uniform and dense. Nano-calcium carbonate incorporation plays physical and chemical effects, reducing the inner area of cement stone to hurry up the first hydration of clinker speed, reducing porosity, increasing the density of cement concrete, and thus improving the compressive strength of concrete [44].

The study shows that the control cement sample lacking ash and nano-silica had the best compressive resistance. This control sample's strength was 58% cement and a couple of steel,40% ash, and nano-silica. Adding huge quantities of ash, particularly greater than 70%, concrete's compressive strength is drastically decreased. Jalal et al, have also checked out high performance [8].

In the study where samples containing nano-silica showed higher strength than samples containing nano-silica ash [33], [13]. The effect of ash on nano silicone on the compressive strength of high-performance compacted concrete [8].

The results show that the addition of ash decreased the strength and also the addition of nano-silica increased the strength. However, the compressive strength of 15% of ash in concrete at 90 days is slightly increased compared to the control. Rahim et al studied the effect on the compressive strength of cementitious concrete containing wood ash by adding nano-silica [27]. Contains a sample containing 2% nano-silica within the presence of wood ash, the effect of nano-silica is little when young, but resistance increases with age. This increase is because of improved pozzolanic reaction. However, during this study, the optimal amount of nano-silica is 1.5%. Windham and Vapilay also investigated the results of nano silica [43], per their research, increasing nano silica increases compressive strength and so decreases it. Therefore, 1.5% gives the very best compressive strength. The rationale for this increase is that the hydration process of tricalcium silicate (C3S) is quicker within the presence of nano-silica. The use of carbonate nanoparticles has been explored, leading to improved mechanical strength, impact resistance, and flexural strength [25].

Another study by Ehsani et al, combined carbonate particles with a carbon coating and investigated the effect on the compressive strength of concrete [25]. This carbon coating is the result of the soot-burning material being combined with lime milk in solution by the reactor. Supported observations, we discover that his 3-day strength of calcium carbonate-bearing concrete with nanocarbon coating shows a decrease in strength compared to the quality sample, as an example, the tenth amount of cement by weight reduces strength by approximately 15.6%. Studies have shown that as concrete ages, the 7-day strength of concrete increases in compressive strength compared to regular concrete specimens. This increase occurs up to three of the burden of the cement, but as this nano fraction increases, the sample undergoes a process of decreasing compressive strength at 7 days old. In addition to the self-cleaning properties of concrete.

Research has shown that the utilization of titanic oxide nanoparticles improves the hydration rate and shortens concrete curing time [10]. Also, the employment of those nanoparticles increases the flexural strength and compressive strength of concrete showing the effect of adding titanium dioxide nanoparticles to the concrete itself [14], [15]. The addition improves the microstructure of concrete and reduces internal voids in concrete, which improves the mechanical properties and durability of concrete [9].

The addition of alumina nanoparticles to the concrete mixture significantly increases the modulus of elasticity of concrete. Experience has shown that adding 10% aluminum nanoparticles increases the modulus of elasticity of concrete by 153%, but has no significant effect on concrete strength [16]. The theoretical and mathematical effects of the addition of aluminum oxide nanoparticles on the hydration of concrete were investigated, and it had been found that the addition of those particles reduced heat release and accelerated the height release time of that heat [28].

The addition of three by weight of corundum nanoparticles to concrete reduces heat to release the foremost [28]. Theoretically and mathematically, the results of the workability of modified concrete containing 0.5, 1.5, 0.5, and a pair of alumina nanoparticles by weight of cement are studied, and also the results show that increasing the number of alumina oxide nanoparticles decreases the workability of concrete. The samples of concrete-containing nano-silica give better results than samples of concrete-containing nano ferrite with an approximate rate of about 10%. The samples of concrete containing granite give better results than similar-containing dolomite and also the approximate rate of about 10%. The utilization of a superplasticizer was necessary for the concrete mixes to boost workability [18].

Table 1. Effect of some important nano-particles on properties of concrete [39].

S/ No.	***Nanoparticles used***	***Improved property of concrete***
1	Nano-silica	○Contributes to reduced emissions of CO2, as the addition of 1 kg micro silica reduced almost 4 kg cement, and this can be higher if nano silica is used ○Offers increased durability to concrete ○Improves compressive strength ○Increases the flexural strength, ○Improves the tensile strength
2	Carbon nanotubes	○Decreases the concrete's final setting time, ○Restricts crack development and propagation at early ages, ○Produces dense concrete, ○Increased quality of bond interaction between aggregates and cement paste ○Increases the compressive strength ○Improves the tensile strength, Young's modulus, flexural strength, and fracture toughness ○Decreases the required size of concrete structural members ○Decreases the early and long-term shrinkage of concrete
4	Nano-TiO2	○Increases the abrasion resistance of concrete ○Improves compressive strength ○Increases the durability of concrete structures ○Increases the flexural strength ○Speeds up the early-age hydration of ordinary ○Portland cement ○Offers self-sensing and self-cleaning properties to concrete structures
5	Nano-Fe2O3	○Improves compressive strength ○Increases the flexural strength ○Improves split tensile strength

		○Reduces the setting time of fresh concrete ○Decreases the total porosity of concrete ○Improves concrete's abrasion resistance
6	Nano-Al2O3	○Increased serviceability ○Increases the modulus of elasticity of concrete. ○Reduced heat release ○Accelerated the height release time of the heat
7	Copper nanoparticles	○Improves formability ○Increases corrosion resistance

3. Effect of nanoparticles on physical properties of concrete

Compressive strength: Based on research, it can be said that nano silica (NanoSiO2) is the most commonly used nanoparticle in a cement matrix, but there are other nanoparticles such as NanoAl2O3, NanoTiO2, NanoFe2O3, NanoFe3O4, NanoClay, NanoZrO2, etc. used. Adding 1, 3, and 5% NanoSiO2 and NanoTiO2 to regular concrete showed a 12% increase in compressive strength for the sample containing 1% nano-silica and an 18% increase for the sample containing 1% nano titanium dioxide. [13], [8]. Another study reported that Zr, Fe, Ti, and Al nano-oxides were used at 1.5 wt% of the cementitious material in super-reinforced concrete, with the best improvement in compressive strength of 55% for samples containing nano-alumina [27]. Adding 0.5 to 2% of nano-silica and nano-alumina and curing in both water and lime water showed that in both cases nano-silica performed better than alumina, with similar results for the treated samples [43]. In another study, nano-silica and micro silica were used in proportions of 1, 3, 5, and 7 in aerated concrete, and nano-silica had a much better effect. A sample containing 7% nano-silica showed a 48% increase in compressive strength [38]. The use of nano Fe_2O_3 at a percentage of 1 to 5 provides the greatest improvement in compressive strength (72% increase with 4% by weight) [30]. Nanosilica dioxide and aluminum are used in ordinary concrete. The optimum percentage of these nanoparticles ware 3% by weight of nano-aluminum oxide and 5% by weight of nano-silicon cement to improve the maximum compressive strength of concrete, 8%, and 30%, respectively [5]. Another study used polypropylene (PP) fibers in addition to nano-silica and nano-aluminum, and the highest improvement was associated with 5% nano-silica, using 2% PP fibers by volume of concrete. The amount of improvement was 31%, slightly greater than the improvement of 5% silica without fibers [11]. The addition of nano-silicon dioxide in amounts of 0.3 and 0.9% by weight of cementitious materials increased the compressive strength of concrete by 9% and 12%, respectively [4]. Another study used 10% by weight nano-silicon cement and showed an approximately 30% improvement in compressive strength [41]. The use of 1% and 2% nano-silica also increased the peak compressive

strength of concrete containing 2% nano-silica with a water-to-cement ratio of 0.39 by 11% [3] in a review article [37].

The use of nano-silica in HPC (high-performance concrete) with body ash of 0%, 1%, 3%, 5%, 7%, and 9% and increasing the number of nano-silica up to five improved the compressive strength of the samples up to 22% in 3 days old samples. And for above 5% of nano-silica like with 7% and 9% of nano-silica, this improvement decreases [6]. In an exceeding study on macro and micro characteristics of concrete through the employment of carbon nanotubes of 0.3%, 0.5%, and 0.75% of the cement weight. The results showed that carbon nanotubes could improve compressive strength by 12% [42]. The development of compressive strength of concrete at the age of three,7, and 28 days showed a major increase. At the age of three days, the compressive strength of concrete that contained nano silica increased between 3.82% - 11.84%; whereas, at the age of seven and 28 days, the compressive strength of concrete with nano silica increased respectively by 3.87% - 17.24% and 4.93% - 24.59%. The resulting splitting enduringness ranges between 13.298 MPa – 19.918 MPa. there's a powerful correlation between concrete's splitting lastingness and compressive strength. The splitting enduringness tends to extend together with the rise of concrete's compressive strength [36].

Modulus of elasticity: The development of compressive strength of concrete at the age of three,7, and 28 days showed a big increase. At the age of three days, the compressive strength of concrete that contained nano silica increased between 3.82% - 11.84%; whereas, at the age of seven and 28 days, the compressive strength of concrete with nano silica increased respectively by 3.87% - 17.24% and 4.93% - 24.59% [36]. With the addition of nano-silica and nano ferrite, the improving percentage of flexural strength and modulus of elasticity of concrete reaches an approximate rate of about 23% and 25%, respectively, with relevance to the control mixes. Increasing the number of NS and NF by quite 3% and a pair of by weight degrades the compressive strength, splitting tensile, flexural strength, and modulus of elasticity of concrete [18].

Durability: Nanosilica is capable of improving the durability of concrete. The rise of 10% nano-silica replacement within the resistance to sulfate attack is healthier than that of 0% nano-silica [35]. In a study reviewed the employment of nanoparticle materials in several styles of concrete was discussed, and conclusions are provided that nanoparticles reduce the permeability of cementitious mixtures against chloride ions; thus, lower values of chloride ion penetration are seen with the incorporation of nanoparticles. The inclusion of nano-scaled particles improves the resistance against freezing and thawing. Using 5% of nano-silica and three nano-alumina reduced the loss of compressive strength by 16.28% and 18.19%, respectively. Various kinds of nanoparticles impose different effects on the shrinkage property of the mixture. The carbonation depth of concrete can obtain

different values with differing types of nanoparticles. The microstructure of various varieties of concrete is significantly enhanced by the addition of nanoparticles since nanoparticles improve the hydration process by producing more hydrated products [29]. A study base on experimental results obtained that coal ash concrete containing NS significantly improved the mechanical properties of concrete specimens relative to a bearing concrete (without NS), which was because of the reaction of NS particles with Ca(OH)2 at the ITZ to provide more C-S-H gel and therefore the densification of the microstructure. However, the optimum amount for every mechanical property was different; the splitting durability reached a maximum when the NS replacement level was 2%, and when the NS replacement level was 3%, the compressive and flexural strengths reached their maximums. Adding NS particles can dramatically improve the impact resistance at the primary cracking of the concrete; however, the speed from initial cracking to failure was faster, and therefore the brittleness of the concrete didn't change. After being impacted, the concrete specimens containing NS were divided into two halves along the impact direction, and also the concrete specimens still exhibited brittle failures, as in ordinary concrete. Compared with the control concrete, the low dosage of NS can greatly ameliorate the concrete's chloride penetration resistance and freezing-thawing resistance. At the two replacement levels, uniform dispersion of NS particles was easily achieved. The development of the pore structures within the concrete and also the filling effect of the NS were liable for the reduction within the chloride diffusion coefficient and ameliorated the freezing-thawing resistance of the concrete [26]. The application of nano-based concrete materials is beneficial concerning enhanced engineering properties of cement materials, particularly for the production of sustainable as well as self-healing concretes.

Density: Based on the results of the research conducted on concrete with the addition of nano-silica as cement partial substitute material, the result is summarized that nano-silica is in a position to extend the density and sturdiness of concrete. In an experimental study adding nanoparticles of the dimensions of but 100 nm into the concrete mix. This study evaluated the utilization of varied nanoparticles in concrete and so compared them to standard concrete. Concrete containing nano silica and nano clay was compared to concrete containing silica fume, fly ash, and slag. The results showed that the microstructure of the nano-silica concrete was denser and more uniform than that of the traditional concrete [24]. In an experimental study on mortar by adding TiO2 nanoparticles of 0.5%, 1.0%, 1.5%, and 2.0% of the cement weight were. the common size of TiO2 nanoparticles was 15 nm. The research results at the age of seven days showed that the nano-TiO2 paste was denser and more compact than that without nano-TiO2 [21].

Abrasion resistance: The use of nano SiO_2, nanoTiO_2, and polypropylene (PP) fibers shows that the lower usage levels of these nanoparticles have better effects on abrasion resistance, and the addition of 1% titanium dioxide was better than 3% and 5%. Improvements of 181%, 148%, and 90% were found, respectively, and the application of 1% nano-silica had a better effect on abrasion resistance than 3% nano-silica, respectively [8]. Another study on Nano SiO_2 and Nano Al_2O_3 used 0.5–2 wt% in water and lime water, and the abrasion resistance of nano silica was better than that of nano alumina. The optimal amount of these materials is 2% by weight of the cementitious material [43]. Different percentages (4%, 8%, and 12%) of nano SiO_2 were added to the colloidal solution, and different amounts (25%-50% at different times and numbers) were also used as sprays 1 to 3 times. Treat with the colloidal solution for 28 days, then test or treat with water and spray onto a clean surface. In each case it contained a higher amount of nano silica of 50% and sprayed 3 times or 12% colloids (showed greater improvement in abrasion tests) Treatment and spraying with colloids containing nanoparticles gave abrasion resistance improvements of 42% and 32%, respectively [33]. The addition of nanoSiO_2 and nano SiC in percentages of 1, 2, and 3 separately and in combination shows that the optimal amount to improve the abrasion resistance in concrete is 2 and 3% by weight of cementitious materials for nano SiO_2 and nano SiC, respectively (49 and 68% improvement, respectively) and the combined mode is the answer better (75% improvement) compared to the separate state [22].Comparison using 40% fine nanoporous material or 5% nano-silica or a combination of 5% nano-silica and 25% fly ash as alternatives to cement. It showed 20%, 16%, and 13% more abrasion resistance for concrete and 82%, 73%, and 68% more abrasion resistance for mortar, respectively [31].

Resistance to permeability and water absorption: The use of silica and titanium nanoparticles and PP (polypropylene) fibers in concrete improved the chloride penetration resistance by 31% and 18% for samples containing 1% nano-titanium dioxide and 1% nano-silica, while PP fibers negatively affected chloride penetration resistance. Also in this study, samples with low levels of nanoparticles showed 1% better improvement than samples with high levels of 3% and 5% against chloride penetration [13]. $NZrO_2$, NFe_3O_4, $NTiO_2$, and HPC concrete with 1.5% nanoparticles of NAl2O3, 80% improvement in water uptake from samples containing NFe_3O_4 and $NTiO_2$ and 70% improvement in chlorinated NZrO2 penetration by NAl2O3 (70%) [27]. In a study on aerated concrete, nano silica by 1%, 3%, 5%, and 7%, and micro silica by 3%, 5%, and 8% were used separately. Micro-silica had a better effect than nano-silica on permeability. The addition of 8% micro-silica showed an improvement of about 25% and the addition of 7% nano-silica also showed a permeability improvement of about 20% [38]. Nanohematite is equivalent to 4%, showing an improvement in water absorption of about 74% [30]. Nanoacids Al_2O_3, Fe_2O_3, Fe_3O_4, and nano clay showed positive effects on the

water absorption of cement mortar, and the authors reported different optimal amounts from 0.5% to 4%, depending on the type of treatment and other materials used in the concrete mix [19]. Nano-silica, nano-alumina, and nano-hematite were put into two types of mortar containing fly ash and silica foam separately, and the compound to be used and its permeability and water absorption were investigated. The addition of 1.25% of nano-aluminum oxide in a mortar containing silica foam has improved 29% of the permeability [23]. Using 1.25% of the three mentioned nanoparticles as combinations described in a fly ash-containing mortar increases the water absorption of the mortar by 14% [32]. Using 0.3% and 0.9% Nano SiO_2 also improves water permeability, so adding 0.3% nano-silica increases the permeability of concrete by 56% [4]. In one study, two types of nano silica were used, one with a fine particle size of 15 nm and the other with a large particle size of 80 nm (each with a 4% difference) (0.5, 1, 1.5, and 2) are used. Water permeability was tested and in the long run, larger nanoparticles showed a superior effect in improving permeability (approximately 23% using 2% of the weight of coarse-grained nano-silica cement) but in the short term, the effect of finer nanoparticles has been better [20]. Nano-silica colloids were used in two different ways (spraying or treatment with nano-silica colloids) to improve permeability, which is the best result for the case where samples were applied in colloids containing 12% nano-silica and 31% improvement in water permeability is shown. Also, the spray of a solution containing nano-silica at a concentration of 50% increased the permeability by 12% [33]. In one study, the effects of Nano SiO_2 on the mechanical properties and durability of concrete were examined in various investigations [7]. Colloidal and powdery modes were used, and the addition of 3.8 wt% nano-silica improved the water permeability by 88% [12].

Frost Resistance: Frost resistance is one of the keys to the durability of concrete, and one of the factors that affect the durability of concrete is the cycle of freezing and thawing. Because the strength of concrete is directly associated with the security and performance of the building structure, its mechanical properties are of concern. To make sure the sturdiness of the building structure within the use of the method, frost resistance in the real world is critical. Consistent with the freezing and thawing of M7.5 specimens, the inner structure of the concrete after adding nanometer material was greatly improved, and also the internal structure of the concrete was improved greatly. The pore size of 150mm disappears from the concrete, greatly increases the interior density of concrete, and avoids structural damage caused by hydrostatic theory and force per unit area theory. Xiaolin Ren and Shunkai Li studied the identical similar comparison test. it was found that under the condition of $-10C^0$, 25 times freeze-thawing was allotted, the incorporation of nanometer material was 0.75% concrete strength loss was 3.2%, and also the reference concrete loss rate was 8.6%, the nanometer material within the concrete, the frost resistance of concrete is improved [36].

4. Discussion

In recent times, advanced nanotechnology has been employed in various sectors for the comfort and welfare of humanity. A majority of the nanostructure-based products applied to date in the concrete sector have numerous advantages. There are several explanations for accepting the fact that nanomaterial usage is rising. Innovative concrete structures need structural components with superior properties, as well as higher durability. The best solution is the incorporation of nanostructured materials in concrete mixes, which could improve the concrete's properties. It should also be noted that nanomaterials are still in their developing stages, and they have many challenges and unsolved complications for their huge commercial prospects.

Nanomaterials such as nano-silica, nano-TiO2, Al2O3, ZnO2, carbon nanotubes, nanofibers, etc. have the capability for increasing the durability of concrete by improving mechanical and thermal properties. The microstructures of various kinds of concrete are remarkably improved by the inclusion of nanomaterials, as the nanomaterials enhance the hydration process by generating more hydrated products. Incorporating various nanomaterials into the concrete mixes decreased the setting time as well as workability, which was due to the stronger reactivity of nanomaterials having a larger surface-to-volume ratio. The decrease in workability of concrete with nanoparticles may be compensated by using of superplasticizer in concrete mixes.

Improvement in compressive strength could be observed with an improvement in the replacement ratio of nanomaterials. This was due to the improved hydration of a more compacted microstructure with the incorporation of finely dispersed nanomaterials. With the incorporation of a nanomaterial such as carbon nanotube (CNT), the concrete compressive strength could be improved to 21%, and also it can result in a decrease in the early as well as long-term shrinking of concrete of 54.0% and 15.0%, respectively. Moreover, the CNT addition to concrete showed 17.0% to 18.0% reduced long-term creep as compared to the concrete with no CNTs. Overall, it was noted that optimum concentrations of nanomaterial incorporation in the concrete could enhance its flexural, tensile, and compressive strength, along with workability and water absorption. With the addition of nano-silica and nano ferrite, the improving percentage of flexural strength and modulus of elasticity of concrete reaches an approximate rate of about 23% and 25%, respectively, with relevance to the control mixes.

Nanomaterials could positively impact the increase in the sustainability and durability of concrete. Nanosilica is capable of improving the durability of concrete. The rise of 10% nano-silica replacement within the resistance to sulfate attack is healthier than that of 0% nano-silica. Different nano-materials could improve the self-healing property of concrete and will restore the weakened constructions in an advanced manner at a lesser expense, relative to that accomplished by epoxy-containing healing products, therefore attaining

ecological sustainability. The reaction of Nano-silica particles with Ca(OH)2 at the ITZ provided more C-S-H gel and therefore the densification of the microstructure could be obtained. The application of specific nanostructured materials could improve the performance of concrete, as well as its life cycle.

Results have been showing that the nano-TiO2 paste was denser and more compact than that without nano-TiO2. The nanomaterial-incorporated concrete could permit the development of ultra-high strength concrete frameworks having higher durability, thereby decreasing the maintenance needs.

It is extremely important to develop an advanced procedure to make sure the appropriate nanomaterial dispersion in commercial-scale field applications. Effective dispersion of nanoparticles is key to achieving the full benefits of adding nanoparticles in a cementitious system.

A rise in the concentration of nanomaterial in the advanced smart nano-based concrete structures greater than the optimum amount was demonstrated to show an adverse impact on the strong performance and durability, which was mostly because of the less compaction, nonuniform dispersion, and development of weaker sections in the concrete. The optimum quantity of incorporated nanomaterials is very important. The optimum addition of appropriate nanomaterial to the concrete can improve mechanical properties such as tensile strength, compressive strength, flexural strength, and durability, etc. of the concrete. For example, the use of nano SiO_2, nanoTiO_2, and polypropylene (PP) fibers shows that the lower usage levels of these nanoparticles have better effects on abrasion resistance. The optimal amount of these materials is 2% by weight of the cementitious material. Freeze–thaw resistance and abrasion resistance of the concrete can also be improved with the addition of nano-silica to the concrete mix. The use of silica and titanium nanoparticles and PP (polypropylene) fibers in concrete improved the chloride penetration resistance by 31% and 18% for samples containing 1% nano-titanium dioxide and 1% nano-silica, while PP fibers negatively affected chloride penetration resistance. Colloidal and powdery modes were used, and the addition of 3.8 wt% nano-silica improved the water permeability by 88%. In a study, it was found that under the condition of $-10C^0$, 25 times freeze-thawing was allotted, the incorporation of nanometer material 0.75% concrete strength loss was 3.2%, and also, the frost resistance of concrete is improved.

Nano-materials can offer concrete structures with self-sensing and self-cleaning abilities. However, the concentration of the nanomaterial present in the concrete should be in a very limited quantity.

5. Findings

The main finding of this paper indicates that the properties of concrete can be significantly improved with the incorporation of various types of nanoparticles.

The application of nano-based concrete materials is beneficial concerning enhanced engineering properties of cement materials, particularly for the production of sustainable as well as self-healing concretes.

It was noted that the nanostructured materials have a higher capability in smart infrastructure applications with superior strength concrete frameworks.

The nanomaterials improve the properties of concrete by the addition of an optimum quantity of incorporated appropriate nanomaterial to the concrete.

6. Future Recommendations

The dispersion of the incorporated nanoparticles is one of the main challenges regarding the use of nanoparticles in the concrete matrix. Thus future studies should focus on finding innovative methods to provide a uniform dispersion of nanoparticles and avoid the formation of agglomerates.

The workability of nanoparticle-induced concrete is recommended. So, research can be performed to obtain the optimum amount of required superplasticizer.

Using nanoparticles in fewer amounts accompanied by waste materials such as plastic aggregates or plastic fibers can be an attractive research study. Further research can be made on the properties of cement-based materials containing both nanoparticles and waste plastic materials to examine long-term properties and improve sustainability. This topic is essential regarding environmental issues due to the accumulation of waste plastic materials.

It is advised to substitute the conventional ordinary Portland cement-based concretes with functional/smart nano-concrete structures for sustainable development.

It was noted that nanomaterials can play an important role in the development of construction materials, and thus proper understanding of these nanomaterials is extremely important. Along with the substantial advancement of nanomaterials in different applications, it should also be noted that nanomaterials are still in their developing stages, and they have many challenges and unsolved complications for their huge commercial prospects. Thus, an investigation can be made to further understand the properties of nano-concretes.

The lack of information on nanomaterial toxicology topics and a tendency to disconnect from prevailing research and development is a significant blockade for its development, to suppress these types of restrictions, organized construction sector-strategic policies should be followed to benefit from the nanomaterials to attain reasonable benefit in particular application extents and the product categories.

7. Conclusion

In this study, the effectiveness of nanoparticles on concrete's performance is discussed, and the following conclusions were drawn:

1) Based on the research, it can be said that nano silica (nanoSiO_2) is the most commonly used nanoparticle in a cement matrix, but there are other nanoparticles such as nano Al_2O_3, nanoTiO_2, nanoFe_2O_3, nanoFe_3O_4, nano clay, nanoZrO_2 carbon nanotubes, nanofibers, and carbon nanofibers.
2) Nano-silica had a much better effect than micro-silica.
3) The nanoparticles improve the strength of concrete. There is a strong correlation between concrete's splitting tensile strength and compressive strength. The splitting tensile strength tends to increase along with the increase of concrete's compressive strength.
4) The addition of nanoparticles to concrete improves the flexural strength and modulus of elasticity of concrete, as with the addition of nano-silica and nano ferrite the improving percentage of flexural strength and modulus of elasticity of concrete reaches the approximate rate of about 23% and 25%, respectively.
5) Nanoparticles are capable of improving the durability of concrete. They increase the resistance to sulfate attack, reducing the permeability of concrete mixtures against chloride ions; improve the resistance against freezing and thawing; reduce the loss of compressive strength; the various types of nanoparticles impose different effects on the shrinkage property and carbonation depth of concrete mixture; the microstructure of different types of concrete is significantly enhanced upon the addition of nanoparticles.
6) Concrete with the addition of nanoparticles as cement partial substitute material showed that the microstructure of the nanoparticles' concrete was denser and more uniform than that of the conventional concrete.
7) Nanoparticles were added to the concrete mixture, they improved its abrasion resistance. The use of nano SiO_2, nanoTiO_2, and polypropylene (PP) fibers shows that the lower usage levels of these nanoparticles have better effects on abrasion resistance.
8) Nanoparticles added to concrete mixtures greatly increase the internal density and resistance to permeability and reduce the porosity of concrete thus the frost resistance and resistance to freezing and thawing are improved. In order ensures the durability of concrete.

References

[1]Balaguru, P. (2005). *Nanotechnology and concrete: Background, opportunities, and challenges.* Paper presented at the Proceedings of the International Conference–Application of Technology in Concrete Design.

[2]Balaguru, P., & Chong, K. Nanotechnology and concrete: research opportunities. *Proceedings of the ACI Session on Nanotechnology of Concrete: Recent Developments and Future Perspectives*. 2006.

[3]Camiletti J, Soliman AM, Nehdi ML. Effect of nano calcium carbonate on early-age properties of ultrahigh-performance concrete. Magazine of Concrete Research. 2013;65:297-307.

[4]Ganesh P, Murthy RA, Kumar SS, Reheman MS M, Iyer N. Effect of nano-silica on durability and mechanical properties of high-strength concrete. *Magazine of Concrete Research*. 2015;68:229-236.

[5]Gopalakrishnan K, Birgisson B, Taylor P, Attoh-Okine N. Nanotechnology in Civil infrastructure, A paradigm shift. Verlag Berlin Heidelberg, Springer, 2011.

[6]Han B, Li Z, Zhang L, Zeng S, Yu X, Han B. Reactive powder concrete reinforced with nano SiO2- coated TiO2. *Construction and Building Materials*. 2017;148:104-112.

[7]Hosseini P, Afshar A, Vafaei B, Booshehrian A, Molaei Raisi E, Esrafili A. Effects of nano-clay particles on the short-term properties of self-compacting concrete. *European Journal of Environmental and Civil Engineering*. 2017;21:127-147.

[8]Jalal M, Pouladkhan R, Harandi O, Jafari D. Comparative study on effects of Class F fly ash, nano silica, and silica fume on properties of high-performance self-compacting concrete, *Construction, and Building Materials*, 2015;94:90-104.

[9]Jalal, M., Fathi, M., & Farzad, M. (2013). Effects of fly ash and TiO 2 nanoparticles on rheological, mechanical, microstructural, and thermal properties of high strength self-compacting concrete. *Mechanics of Materials, 61*, 11-27.

[10] Jayapalan, A., Lee, B., & Kurtis, K. (2009). Effect of nano-sized titanium dioxide on early age hydration of Portland cement *Nanotechnology in Construction 3* (pp. 267-273): Springer.

[11] Khaloo A, Mobini MH, Hosseini P. Influence of different types of nano-SiO2 particles on properties of high-performance concrete. *Construction and Building Materials*. 2016;113:188-201.

[12] Langaroudi MAM, Mohammadi Y. Effect of nano-clay on workability, mechanical, and durability properties of self-consolidating concrete containing mineral admixtures. *Construction and Building Materials*. 2018;191:619-634.

[13] Li G. Properties of high-volume fly ash concrete incorporating nano-SiO2. *Cement and Concrete research*. 2004;34:1043-1049.

[14] Li, H., Zhang, M.-h., & Ou, J.-p. (2007). Flexural fatigue performance of concrete containing nano-particles for pavement. *International Journal of Fatigue, 29*(7), 1292-1301.

[15] Li, H., Zhang, M.-h., & Ou, J.-p. Abrasion resistance of concrete containing nano-particles for pavement. *Wear, 260*(11), 2006. 1262-1266.

[16] Li, Z., Wang, H., He, S., Lu, Y., & Wang, M. (2006). Investigations on the preparation and mechanical properties of the nano-alumina reinforced cement composite. *Materials Letters, 60*(3), 356-359.

[17] Li, Zongjin, *Advance concrete technology*, John Wiley & Sons, INC, New Jersey. 2011.

[18] Mohamed A. and Khaled A., Effect of using different types of nanomaterials on mechanical properties of high strength concrete, *Elsevier, Construction and Building Materials 80,* (2015), pp.116–124

[19] Nazari A, Riahi S, Riahi S, Shamekhi SF, Khademno A. An investigation on the Strength and workability of cement-based concrete performance by using ZrO2 nanoparticles. *Journal of American Science*. 2010;6:29-33.

[20] Nazari A, Riahi S, Riahi S, Shamekhi SF, Khademno A. Influence of Al2O3 nanoparticles on the compressive strength and workability of blended concrete. *Journal of American Science*. 2010;6:6-9.

[21] Nazari A., The effects of curing medium on flexural strength and water permeability of concrete incorporating TiO2 nanoparticles, *Materials, and Structures*, 2011, 44:773–786.

[22] Niewiadomski P, Hoła J, Ćwirzeń A. Study on properties of self-compacting concrete modified with nanoparticles. *Archives of Civil and Mechanical Engineering*. 2018;18:877-886.

[23] Norhasri MSM, Hamidah MS, Fadzil AM. Applications of using nanomaterial in concrete: A review. *Construction and Building Materials*. 2017;133:91-97.

[24] Ozyildirim, Celik, Laboratory Investigation of Nanomaterials to Improvethe Permeability and Strength of Concrete, Virginia Transportation Research Council, 530 Edgemont Road,Charlottesville, VA 22903-2454, www,vtrc,net, 2010. (434) 293-1900.

[25] Parveen S, Rana S, Fangueiro R. A Review on Nanomaterial Dispersion, Microstructure, and Mechanical Properties of Carbon Nanotube and Nanofiber Reinforced Cementitious Composites, *Journal of Nanomaterials*, 2013.

[26] Peng Z., Dehao S., Qingfu L., Shikun Z, and Yifeng L., Effect of Nano Silica Particles on Impact Resistance and Durability of Concrete Containing Coal Fly Ash, *Nanomaterials*, 2021, pp. 1-19.

[27] Raheem A, Ikotun B. Investigation of Workability and Compressive Strength of Wood Ash Cement Concrete Containing nano-silica. *Advanced Materials Research*. 2019;1154:129-136.

[28] Rashad, A. M. A synopsis about the effect of nano-Al 2 O 3, nano-Fe 2 O 3, nano-Fe 3 O 4, and nano clay on some properties of cementitious materials–a short guide for Civil Engineer. *Materials & Design*, 2013, *52*,143-157.

[29] Rawa A. M. and Niyazi U. K., Nanoparticles used as an ingredient in different types of concrete, SN *Applied Sciences*, (2021) pp. 1-17.

[30] Ren J, Lai Y, Gao J. Exploring the influence of SiO2 and TiO2 nanoparticles on the mechanical properties of concrete. *Construction and Building Materials*. 2018;175:277-285.

[31] Ruan Y, Han B, Yu X, Li Z, Wang J, Dong S. Mechanical behaviors of nano-zirconia reinforced reactive powder concrete under compression and flexure. *Construction and Building Materials*, 162, 663-673

[32] Ruan Y, Han B, Yu X, Zhang W, Wang D. Carbon nanotubes reinforced reactive powder concrete. Composites Part A: *Applied Science and Manufacturing*. 2018;1112:371-382.

[33] Said L, Zeidan M, Bassuoni MT, Tian Y. Properties of concrete incorporating nano-silica. *Construction and Building Materials*. 2012;36:838-844.

[34] Saleem, H.; Zaidi, S.J.; Alnuaimi, N.A. Recent Advancements in the Nanomaterial Application in Concrete and Its Ecological Impact. Materials **2021**, 14, 6387. https://doi.org/10.3390/ma14216387

[35] Saloma, Amrinsyah N., Iswandi I. and Mikrajuddin A. Improvement of concrete durability by nanomaterials, The 5th International Conference of Euro Asia Civil Engineering Forum (EACEF-5), *Elsevier*, 2015, pp. 608-612

[36] Saloma, Amrinsyah N., Iswandi I., and Mikrajuddin A., Experimental Investigation on Nanomaterial Concrete, *International Journal of Civil & Environmental Engineering (IJCEE-IJENS)* Vol:13 No:03, June 2013, pp 15-20.

[37] Shaikh FUA, Supit SWM. Mechanical and durability properties of high volume fly ash (HVFA) concrete containing calcium carbonate (CaCO3) nanoparticles. *Construction and Building Materials*. 2014;70:309-321.

[38] Sivasankaran U, Raman S, Nallusamy S. Experimental Analysis of Mechanical Properties on Concrete with Nano Silica Additive. *Journal of Nano Research*. 2019;57:93-104.

[39] Sobolev K. Nanotechnology in Construction. 2015. Nanotechnol Constr. https:// doi. org/ 10. 1007/ 978-3- 319- 17088-6

[40] Sun J, Shen X, Tan G, Tanner. Modification Effects of Nano-SiO2 on Early Compressive Strength and Hydration Characteristics of High-Volume Fly Ash Concrete. *Journal of Materials in Civil Engineering*. 2019;31:04019057.

[41] Uthaman S, Vishwakarma V, George RP, Ramachandran D, Kumari K, Preetha R, *et al*. Enhancement of strength and durability of fly ash concrete in seawater environments: Synergistic effect of nanoparticles. *Construction and Building Materials*. 2018;187:448-459.

[42] Valquíria S, M., José M.F., Calixto, Luiz O., Ladeira, dan Adriano P, Silva, Macro and Micro Characterization of Mortars Produced with Carbon Nanotubes, *ACI Materials Journal*, May-June 2011.

[43] Vandhiyan R, Pillai E.B. Influence of Nano Silica Addition on the Behavior of Concrete and Its Impact on Corrosion Resistance. *Journal of Computational Theoretical Nanoscience*. 2018;15:530-536.

[44] Wei L., Linkai X., Xiaochu W., and Yi R., A Review of Mechanical Properties and Durability of Nano-concrete, *Advances in Engineering Research*, Volume 136, (7th ICADME) 2017, pp. 5-8.

Author Profile:



NOORULLAH ZAHID received the B. Tech. degree in the department of civil engineering from Nangarhar University in 2004, Nangarhar, Afghanistan, and completed the M. Tech. degree in the division of structural engineering of the civil department from the National Institute of Technology Warangal (NITW) in 2012, Warangal, Telangana, India. Currently, He is working as an Assistant Professor in the Department of Civil Engineering at Shaikh Zayed University, Khost, Afghanistan. His areas of research include Civil Engineering.